



# MIROTONE

Leading the way in coating systems since 1938

## Data Sheet

Date of Issue	30 Jun 2009
Document Ref	3720
Version No	47
Date Printed	30 Jun 2009

## MIROBILD AC 3720 Pigmented Undercoat



### Important Information

Mirotone only warrants the quality of the product in the can. It is your responsibility as the user, before application, to ensure that the coating system meets your requirement and is fit for the intended purpose.

### Product Description

MIROBILD AC 3720 is a pigmented acid catalysed undercoat for use on medium density fibreboard (MDF), particleboard or wood. It has excellent high build, ideal when a full finish is required, whilst the ease of sanding provides fast throughput during production. A special design feature of this product is its compatibility with MIROBILD AC 3750 & 3770 pigmented topcoats. Excess MIROBILD AC 3750 & 3770 topcoat can be added into MIROBILD AC 3720 to create a tinted undercoat. This improves coverage and reduces cost and wastage. This product is designed for interior use only.

### Features & Benefits

<b>Excellent Flow:</b>	Provides an excellent base which requires less sanding, resulting in a smooth level finish for the approved topcoats.
<b>High Build:</b>	Enhances the finished appearance of the topcoat and can be applied directly over MDF to seal the fibres.
<b>Easy to Sand:</b>	Results in minimal sanding time, less coating waste and low sandpaper consumption.
<b>Excellent Coverage:</b>	MIROBILD AC 3720 coloured undercoats provide the highest coverage possible, this reduces labour and material costs.

### Typical Applications

- Solid & Veneer Wood Fixtures
- Built-in Wardrobes
- Commercial & Domestic Furniture

### Product Properties

<b>Colour</b>	White
<b>Tinted Undercoat</b>	MIROBILD AC 3750 & 3770 topcoat may be added to MIROBILD AC 3720 to tint the undercoat. See the "Tinted Undercoat" section for mixing instructions.
<b>Coloured Undercoat</b>	If a pre-coloured undercoat is required, Mirotone can supply a range of coloured undercoats to suit your requirements. See the "Tinted Undercoat" section for colour availability.
<b>Gloss Level</b>	Undercoat
<b>Vertical Hang-Up</b>	Excellent
<b>Solvent Resistance</b>	Excellent
<b>Sandability</b>	Excellent
<b>Build</b>	High Build
<b>Water Resistance</b>	Excellent
<b>Hardness</b>	Maximum after 7 days
<b>Levelling &amp; Flow</b>	Excellent
<b>Sink Back</b>	Minimal

### Application Methods

<b>Suction Gun</b>	Use 1.5 to 2mm (59 - 79 thou) orifice with 350-400kpa (50-55 psi).
<b>Pressure Pot</b>	Use 1.5 to 2mm (59 - 79 thou) orifice with pressure pot air-cap. Gun pressure 350-400kpa (50-55 psi) and a pot pressure of 45kpa (6 psi) max.
<b>Airless Spray</b>	Use 0.23 to 0.33mm (9 - 13 thou) orifice, 15cm fan (dependent on job) with regulated pump pressure of 350-400kpa (50-55 psi).
<b>Air Mix Guns</b>	Settings similar to airless spray with the air-assisted regulator pressure at 70-90kpa (10-15psi).
<b>Curtain Coating</b>	Viscosity 40-50 seconds. Consult your local representative for further information.

Mirotone recommends a range of spray equipment. Please contact your Mirotone representative for information on equipment for your application.

### Mixing Ratio

10 Parts MIROBILD AC 3720 Part A Base : 1 Part MIROBILD AC 3800 Universal Catalyst or MIROBILD AC 3810 Quick Dry Catalyst by volume. Mix A & B and then add thinner.

**Digestion Time:** Allow mixed A & B product to stand and react for 15 minutes prior to thinning. This will ensure that maximum film hardness and clarity is obtained. Failure to allow time for the reaction to take place may result in a hazy film.

### Pot Life

1 day at 25°C.

**Note:** Pot life varies with ambient temperature conditions, it is longer at lower temperatures and shorter at high temperatures.

### Recommended MIROSOL® Thinners

**Thinner Rating Guide**

••• Highly Recommended

•• Recommended

• Approved

**Note:** MIROSOL Thinners with a 'Highly Recommended' rating will result in the longest pot life.

Speed of Dry (Listed Fastest to slowest)	Suitability	MIROSOL Thinner	Aromatic Free?	Pack Size Available			
				4 Litre	20 Litre	60 Litre	205 Litre
Ultra Fast	•	MIROSOL 1204	Yes		*	*	
	••	MIROSOL 1234	Yes		*	*	
	••	MIROSOL 1286	No		*	*	*
Fast	••	MIROSOL 1222	No	*	*	*	*
	••	MIROSOL 1280	No		*	*	
	••	MIROSOL 1232	Yes	*	*	*	
	•••	MIROSOL 1220	Yes	*	*	*	*
	•••	MIROSOL 1225	Yes		*	*	
	••	MIROSOL 1217	Yes	*	*		
Medium	••	MIROSOL 1252	Yes	*	*		
	•••	MIROSOL 1294	Yes	*	*	*	
	••	MIROSOL 1265	Yes	*	*	*	
Slow	••	MIROSOL 1266	Yes	*	*	*	
	•••	MIROSOL 1242	No	*	*	*	
	••	MIROSOL 1260	Yes	*	*	*	
Ultra Slow	•	MIROSOL 1218	No	*	*	*	
Specialty Reducers	••	MIROSOL 1297 Retarder	No	*			

**Thinner Reduction Rate**

Thin up to 20% depending upon application requirements.

**Note:** In hot or draughty conditions Mirotone recommends that no more than 10% Ultra Slow Thinners is added. Exceeding this amount will retard the drying and could lead to problems with sanding, printing and blocking. Use faster thinners to achieve required viscosity and then use (only if required) a small amount of Ultra Slow Thinner to improve flow and levelling.

**Application Viscosity & Wet Film Thickness**

Spray only in properly constructed and compliant spray booth.

**Spraying Viscosity:** 40-50 seconds BS4 Flow Cup at 25°C.

**Wet Film Thickness:** 150-200 microns wet film thickness per coat.

**Approximate Drying Times @ 23°C**

**Dust Free:** 10-15 minutes

**Touch Dry:** 20-30 minutes

**Sanding:** 2½-3 hours

**Hard Dry:** Overnight

**Block Stacking:** 24 hours

**Full Cure:** 7 days



**Note:** Low temperatures or heavy film thickness will retard drying times and cause frying upon application of subsequent coats.

**Force Drying Procedure**

**Flash Off:** 5 minutes @ 20°C

**Force Dry:** 30 minutes @ 40-60°C (dependent on airflow)

**Cool Down:** 5 minutes @ 20°C

The above temperatures are dependent on airflow.

**Shelf Life**

**Pack A** - 12 months in sealed containers

**Pack B** - 6 months in sealed containers

All products must be stored in sealed containers below 35°C.

**Coverage (theoretical)**

6-7 m<sup>2</sup> per litre when applied with a conventional spray gun at 150 micron wet film build applied at 40 seconds BS4 application viscosity. These measurements are dependent on the application equipment / gun set-up and the articles being coated.

**Note:** The coverage above is the maximum rate possible and will vary dependent on the application equipment and total wastage.

**Packaging**

Product	Can Size	Net Contents

MIROBILD AC 3720	4 Litre 20 Litre	4 Litre 20 Litre
MIROBILD AC 3800	500ml 1 Litre 2 Litre 4 Litre 20 Litre	400ml 1 Litre 2 Litre 4 Litre 20 Litre

### Application Equipment Clean Up

Clean all equipment immediately after use with any of the MIROSOL thinners listed below. Do not leave MIROBILD AC acid catalysed, MIROTHANE PU polyurethane or MIROPOL PE polyester coatings in your equipment longer than the recommended pot life as this could result in the equipment becoming unusable.

#### Gun / Equipment Wash Rating Guide

••• Highly Recommended      •• Recommended      • Approved

Speed of Dry (Listed Fastest to slowest)	Rating	Thinner	Aromatic Free?	Pack Size Available			
				4 Litre	20 Litre	60 Litre	205 Litre
Ultra Fast	•••	MIROSOL 1208	Yes		*	*	*
	••	MIROSOL 1215	Yes		*	*	*
	•••	MIROSOL 1234	Yes	*	*	*	*
	•	MIROSOL 1286	No		*	*	*
Fast	•	MIROSOL 1222	No	*	*	*	*
	•••	MIROSOL 1224	Yes	*	*	*	
	••	MIROSOL 1280	No	*	*	*	
	•••	MIROSOL 1232	Yes		*		
	•	MIROSOL 1220	Yes	*	*	*	*
	•	MIROSOL 1225	Yes		*		
	•••	MIROSOL 1217	Yes	*	*		
Medium	•	MIROSOL 1252	Yes	*	*		
	•	MIROSOL 1294	Yes	*	*	*	
	•	MIROSOL 1263	No	*	*	*	
	••	MIROSOL 1265	Yes	*	*	*	
Slow	••	MIROSOL 1266	Yes	*	*	*	

### Application System

#### Surface Preparation

All wood and wood related substrates must be free from dust, grease, dirt and all other contaminants before proceeding. Contaminants may be removed by washing the substrate with MIROSOL 1231 Medium Thinner which is ideal for removing wax and grease. Fill all wood defects with MIROPUTTY 916 water based wood filler (i.e. cracks, holes, etc) or fill open grain woods with MIROFIL 1702, if full high build finish is required.

#### Sanding

Wood Substrates - Sand to a smooth even finish using 180-240 grit 3M Production Fre-cut paper.  
MDF Boards - Sand to a smooth even finish using 240-320 grit 3M Production Fre-cut paper.  
Remove all sanding dust using an air gun and clean lint free cloths.

#### Undercoating

Undercoat substrate with MIROBILD AC 3720 as per the instructions detailed on this data sheet.  
Allow 1-2 hours to dry and then sand with 280-320 grit 3M Production Fre-cut paper.  
Remove all sanding dust using an air gun and clean lint free cloths.  
Once sanded MIROBILD AC 3720 must be topcoated the same day.

#### Topcoat

Topcoat with MIROBILD AC 3750 or 3770 as per the instructions on the relevant data sheet.  
Allow 1-2 hours to dry and then sand with 320-400 grit 3M Production Fre-cut paper.  
Remove all sanding dust using an air gun and clean lint free cloths.  
Apply a second coat of MIROBILD AC 3750 or 3770 pigmented topcoat.  
**Note:** If the MIROBILD AC 3720 has been mixed with the Part B catalyst for more than 6 hours, thoroughly sand with 400 grit Fre-cut paper to create adequate intercoat adhesion and to remove any dust particles and surface defects.

#### Tinted Undercoat

MIROBILD AC 3720 undercoat can be purchased in one of the following colours below:

- 2060 Light Grey
- 5071 Pastel Yellow
- 7024 Rusty Pink
- 8049 Sky Blue
- 9041 Pale Green
- 0001 White

To create your own tinted undercoat is it possible to add left over MIROBILD AC 3750 or 3770 topcoat into MIROBILD AC 3720 undercoat at the following addition rate (amount below makes one litre of coloured undercoat):

MIROBILD AC 3720 White Undercoat	MIROBILD AC 3750 or 3770 Pigmented Topcoat	MIROBILD AC 3800 Catalyst	Thinner amount
70% : 700ml	30% : 300ml Max	100ml	15% : 150ml

## Warnings

**!** **Follow Directions:** Carefully read the contents of this Data Sheet and the associated Material Safety Data Sheet (MSDS). Please do not apply this product unless:

- You have a Material Safety Data Sheet (MSDS) in your possession.
- You fully understand these important documents, and
- You are prepared to follow all directions.

**!** **Not Recommended:** This product is not recommended for the following applications:

- Exterior exposure
- Bar and counter tops
- Kitchen bench tops
- Bathroom vanity tops
- High humidity and / or wet areas

**!** **Harsh In-Service Environments:** For harsh in-service environments Mirotone recommends the use of MIROTHANE PU 5545 Clear sealer with MIROTHANE PU 5555 Clear topcoat or MIROTHANE PU 5625 or MIROPOL PE 5110 & 5111 pigmented undercoat with MIROTHANE PU 5650 or 5605 pigmented topcoat.

**!** **Damage caused by sharp objects:** Coatings can be damaged by sharp objects. Due care should be taken in harsh in-service environments to protect the coating e.g. use placemats, coasters, table cloths or other protective coverings.

**!** **Recommended Coating System:** For superior coating properties and in-service performance, Mirotone recommends the application of one sealer coat followed by two coats of an approved topcoat. Alternatively for high volume production environments a two sealer / one topcoat system may be used but this will lead to reduced physical properties of the coating system. In clear coating systems excessive application of sealer or topcoat may result in milky or cloudy appearance in the final finish.

**!** **MIROSOL Thinners:** The use of any thinner other than the approved list on this data sheet will void any warranty that Mirotone may offer. Refer to Mirotone's Technical Bulletin "Mixed Coating Systems".

**!** **High Humidity and Moisture In-Service Environments:** All wood will swell and discolour if allowed to come into contact with water vapour. The protection provided by a coating is dependent on the moisture transmission of the coating and on the thickness of the dry coating film applied. Coated sharp edges are usually the most vulnerable to damage either from the coating being removed or by inadequate film builds in high wear / traffic areas. Special care during sanding and coating should always be given to sharp edges as the coatings do not build as well onto them, resulting in reduced protection in high moisture environments.

**!** **Damp Wood:** Do not apply coatings over damp wood (moisture content greater than 15%) as the following may result:

- Loss of adhesion to the wood
- Cracking or veneer checking of the wood
- Frying of the coating system, particularly with Acid Catalysed systems

**!** **High Humidity at Time of Application:** Application of coatings at high humidity will:

- Speed up the drying process and reduce the pot life of polyurethane coatings.
- Increase the risk of blooming (whitening).
- Blooming may occur if the coating is applied over damp wood or exposed to water or dew during the first hour of drying.

**!** **Milkiness:** Coating systems using multiple coats of any sealer will increase the risk of the dry film appearing milky (especially when applied over dark stains or woods) and may result in white marking if the film is damaged by sharp objects.

**!** **Cold Temperature:** Application of any coating at low temperatures will reduce the general in-service performance of the coating due to reduced cross linking of the coating. Application of MIROTHANE PU or MIROPOL PE below 15°C and MIROCAT PC or MIROBILD AC below 10°C may affect drying and the gloss level of the coating.

**!** **Inter-coat Adhesion:** To ensure sound inter-coat adhesion, thoroughly sand between coats. To reduce the potential for adhesion failure in the field, Mirotone strongly recommends it's customers carry out regular and appropriate quality control testing of their production output.

**!** **Bridging:** On routed MDF panels and doors DO NOT exceed the recommended wet film thickness, as cracking or bridging of the dry film in the grooves may occur.

**!** **Digestion Time:** Ensure that the mixed A & B packs are allowed to stand for 15 minutes prior to addition of thinner and stain and prior to application.

**!** **Catalysed Coatings:** The chemical resistance of a coating reduces as the time interval between catalysing the coating and applying the coating increases. The performance properties of MIROBILD AC coatings will gradually deteriorate throughout the length of their pot life. MIROCAT PC 3244 when catalysed will gradually lose the chemical resistance benefits with all benefits being lost after 2 days.

**!** **Gloss Level:** Care must be taken to apply a uniform wet film thickness (WFT). Gloss level is dependent on WFT and will be lower at low WFT and higher at high WFT.

**!** **Handling:** The transfer of oils or fats from the skin to the surface of the coating may leave visible finger prints on dry coatings. The lower the gloss level and the darker the colour the more visible the finger prints will be. Therefore use of dark low gloss colours should be carefully considered. In most cases Mirotone's Sprayglow will remove finger prints.

**!** **Buffing:** To improve gloss level of topcoats use light hand or machine buffing/polishing with the 3M Perfect IT polishing system. If sanding of the coating is required to remove surface defects, the panel must be sanded and resprayed in a dust free environment.

**!** **Discolouration:** Always test the substrate before application as many timbers or veneer/glue combinations discolour when coated with Acid Catalysed coatings (i.e. Huon Pine, Myrtle, Tasmanian Blackwood or Beech). It may take some time for the effect to occur. In order to reduce the risk of discolouration apply MIROSTOP 3511/MIROPRIME 3512 as a barrier coat directly over the substrate or use one of Mirotone's MIROTHANE PU polyurethane clear coating systems.

**!** **In Can Appearance:** Clear coatings in subdued gloss levels (matt, satin & semi-gloss) may have a slightly milky in-can appearance.

**!** **Over Catalysing:** Do not over catalyse MIROBILD AC coatings as this may cause the coating to become brittle, thereby increasing the risk of cracking. It will also increase the risk of the coating becoming milky in high humidity environments.

**!** **Packaging:** Any two component coating mixed with a slow hardener or retarder thinner will require increased drying time before packaging. The same Part B must be used on the entire job to ensure a visually consistent finish.

## Health & Safety

Refer to Material Safety Data Sheet (MSDS). MSDS sheets are available at [www.mirotone.com](http://www.mirotone.com)

**Ensure that all Personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.**

**Engineering Controls:** Avoid inhalation of vapour or sanding dust by maintaining adequate ventilation. Avoid pockets of vapour. This is normally achieved by applying in a well-exhausted spray or sanding booth complying with AS 4114. If inhalation risk exists (e.g. spraying) the operator must wear a half-face respirator complying with AS1716 (type A/P) and use in accordance with AS1715.

**Personal Protection:** Contact with any chemical should be avoided. Avoid contact with skin and eyes, and avoid breathing the vapour or spray mist. Wear suitable protective clothing including rubber or PVC gloves and safety goggles. When using, do not eat nor smoke.

### Mirotone Accreditations

**Research Laboratory:** Mirotone's head office research laboratory in Sydney, Australia holds N.A.T.A. accreditation No. 865 under ISO/IEC 17025:1999 General Requirements for the Competence of Testing and Calibration Laboratories.  
N.A.T.A. - National Association of Testing Authorities

**Quality System:** Mirotone is N.A.T.A. certified to AS/NZS ISO 9001:2000 Quality Systems for design and manufacturing.

### Mixed System Policy

**A Mixed System is:**

Where any coating or additive manufactured by another coating manufacturer is applied under, between, in, or on top of, coatings manufactured by Mirotone. [Additives may include thinners, retarding solvents, hardeners, flow additives, stains or catalysts]; or

Where products manufactured or supplied by Mirotone are used in a manner not approved or recommended by Mirotone on its labels or Data Sheets.

**Policy:** Mirotone will not recognise any warranty claim from customers or third parties if any Mirotone product has been used in a Mixed System. Mirotone can only warrant the quality of its own range of coatings when used in strict accordance with the recommended coating systems thinners and additives stated on Mirotone's labels and Data Sheets.

### Limitation of Liability

**This Data Sheet is based on information in Mirotone's possession at the "Date of Issue" above. Later experience may lead to amendments. Users should check with Mirotone to ensure that this Data Sheet is still current.**

The information contained in this Data Sheet is based on data appraised in our Laboratories and on our own research, and that of others whose work we believe is reliable. Due to possible differences between controlled laboratory test conditions and methods, and actual application conditions and methods, coupled with possible differences in interpretation of results, the user of this product must satisfy himself that the end result obtainable under his particular application conditions meets his requirements. Special attention is directed to the problem of chemical compatibility, as Mirotone can control only the quality and formulation of its own materials. Mirotone has no control over quality, formulation or consistency of other manufacturers' products or the substrate to which its product is applied. Therefore Mirotone supplies its products only on condition that the consumer himself is satisfied as to the performance of the product in meeting his particular requirements.

### Mirotone Contact Details

#### Australia (Mirotone Head Office)

Mirotone Pty Ltd  
21 Marigold Street  
Revesby, NSW, 2212  
Australia  
PH: +61 2 9795 3700  
Fax: +61 2 9771 3601

#### Malaysia

Mirotone (Malaysia) Sdn. Bhd.  
No. 9 Jalan Sejahtera 25/124 Section 25  
Axis Premier Industrial Park  
40400 Shah Alam, Selangor  
Malaysia  
PH: +60 3 5124 6136  
Fax: +60 3 5124 6137

#### China

Guangzhou Haosen Trading Co Ltd  
Rm 2705, B Building, Gao Ke Mansion  
North of Tian He Road Guangzhou  
Guangdong  
China  
PH: +86 20 3828 9789  
Fax: +86 20 3828 8210

#### New Zealand

Mirotone (NZ) Ltd  
32 Cryers Road  
Auckland 1730  
New Zealand  
PH: +64 9 272 2730  
Fax: +64 9 272 2733

#### Chile

South Trading & Services S.A.  
Avda. Ricardo Lyon 3505  
Nunoa, Santiago  
Chile  
PH: +56 2 205 5412  
Fax: +56 2 223 4369

#### Philippines

Cebu Furnitech Marketing Inc  
Francisco Yang Building  
Warehouse #1 & 2 Mabini Street  
Looc, Mandaue City 6014  
Cebu Philippines  
PH: +63 3 2420 2968  
Fax: +63 3 2346 0616

#### India

Forhands International  
3 Kothari Complex  
Basni Road, Opp Diesel Shed  
Jodhpur-342005 (Rajasthan)  
India  
PH: +91 291 325 0563  
Fax: +91 291 263 7148  
Email: [forhandsinternational@gmail.com](mailto:forhandsinternational@gmail.com)

#### Thailand

Mirotone (Thailand) Co., Ltd.  
83 Moo 4 Poochaosamingprai Rd  
Samrong Klang, Prapradaeng  
Samutprakarn 10130  
Thailand  
PH: +66 2 754 4451  
Fax: +66 2 754 4450

[www.mirotone.com](http://www.mirotone.com)

