

Conbextra C

General purpose, flowable, dual shrinkage compensated cementitious grout - (gaps 10 mm to 100 mm thickness)

USES

Conbextra C is a Type C Class, dual shrinkage control, cement based grout used for general purpose grouting where it is essential to eliminate shrinkage when completely filling the void between a base plate and a substrate.

ADVANTAGES

- Dual expansion system compensates for shrinkage in both the plastic and hardened states
- High ultimate strength and low permeability ensure the durability of the hardened grout
- Can be dry packed/rammed, trowelled, flowed and pumped
- Hydrogen free gas expansion
- Prepackaged material overcomes potential on-site mixing variations
- No metallic iron content to cause rusting

DESCRIPTION

General purpose shrinkage compensated cementitious grout, is supplied as a ready to use dry powder. The addition of a controlled amount of clean water produces a flowing shrinkage compensated grout for gap thicknesses from 10 mm up to 100 mm.

Conbextra C is a blend of Portland cement, specially graded fillers and additives which impart controlled expansion in the plastic and hardened state whilst minimising water demand. The low water demand ensures high early strength. The graded filler is designed to assist uniform mixing and produce a consistent, flowable grout. Maximum aggregate size for pumping is 0.3 mm.

STANDARDS COMPLIANCE

Meets the following standards:

SAA MP20 - Part 3 - Class C Grout
AS2073 (1977) - Clauses 10 and 17

TECHNICAL SUPPORT

Parchem offers a comprehensive range of high quality, high performance construction products. In addition, Parchem offers technical support and on-site advice to specifiers, end-users and contractors.

PROPERTIES

Consistency	Water Addition (Litres)	Compressive Strength (MPa) (AS 2073)			Yield (Litres)
		1	7	28	
		Day	Days	Days	
Dry Pack	2.0 - 2.6	40	60	70	10.20
Trowellable	2.6 - 3.2	30	50	65	10.40
Flowable	3.2 - 4.0	20	45	60	10.88

The above tests were carried out at 23°C.

Note: compressive strengths stated were obtained under controlled conditions at bottom end water, e.g: the 28 day strength of 60 MPa for flowable consistency was obtained at 3.2 litres water per 20 kg bag of Conbextra C.

FRESH WET DENSITY

Approximately 2200kg/m³ depending on actual consistency used.

EXPANSION CHARACTERISTICS

- An expansion between 1 - 3% overcomes plastic settlement in the unset material
- Longer term expansion in the hardened state is designed to compensate for drying shrinkage

TIME FOR EXPANSION

Plastic state:	start	15 minutes
	finish	initial set
Hardened state:	start	initial set
	finish	up to 28 days

SPECIFICATION CLAUSES

PERFORMANCE SPECIFICATION

The premixed proprietary grout must meet the following standards.

All grouting shown on the drawing must be carried out with a pre-packaged cement based product which is chloride and hydrogen gas free

It shall be mixed with clean water to the required consistency. The grout must not bleed or segregate when mixed.

A positive volumetric expansion shall occur once the grout has been placed and cured.

The compressive strength of the grout must exceed 45 MPa at 7 days and 60 MPa at 28 days at a flowable consistency.

The storage, handling, placement and curing of the grout must be in strict accordance with the manufacturer's instructions.

SUPPLIER SPECIFICATION

All grouting where shown on the drawing must be carried out using Conbextra C manufactured by Parchem and used in accordance with the manufacturer's current Technical Data Sheet.

APPLICATION INSTRUCTIONS

PREPARATION

FOUNDATION SURFACE

The substrate surface must be free from oil, grease or any loosely adhered material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown clean of any dirt or debris.

PRE-SOAKING

Several hours prior to grouting, the area of cleaned foundation should be flooded with fresh water. Immediately before grouting takes place, any free water should be removed with particular care being taken to blow out all bolt holes and pockets.

BASE PLATE

It is essential that this is clean and free from oil, grease or scale. Air pressure relief holes should be provided to allow venting of any isolated high spots.

LEVELLING SHIMS

If these are to be removed after the grout has hardened, they should be treated with a thin layer of grease.

FORMWORK

The formwork should be constructed to be leakproof. This can be achieved by using foam rubber strip or construction silicone sealant beneath the constructed formwork and between joints.

In some cases it is practical to use a sacrificial semi-dry sand and cement formwork. The formwork should include outlets for pre-soaking.

UNRESTRAINED SURFACE AREA

This must be kept to a minimum. Generally the gap width between the perimeter formwork and the plate edge should not exceed 150 mm on the pouring side and 50mm on the opposite side. It is advisable where practical to have no gap at the flank sides.

MIXING AND PLACING

MIXING

For best results a mechanically powered grout mixer should be used. When quantities up to 40 kg are used, a slow speed drill fitted with a high shear mixer is suitable. Larger quantities will require a high shear vane mixer. Do not use a colloidal impeller mixer.

To enable the grouting operation to be carried out continuously, it is essential that sufficient mixing capacity and labour are available. The use of a grout holding tank with provision to gently agitate the grout may be required.

PLACING

At 23°C place the grout within 20 minutes of mixing to gain full benefit of the expansion process.

Conbextra C can be placed in thicknesses from 10 mm up to 100 mm in a single pour when used as an underplate grout. Where the grouting gap beneath the base plate exceeds the maximum thickness allowed, then the grout can be filled / bulked out with Conbextra Grout Aggregate* to minimise exotherm heat build up. Alternatively Conbextra Deep pour is available for pours up to 500 mm thick.

Filling / bulking out of the grout should not exceed a ratio of 2 : 1 grout to aggregate. The addition of aggregate will change the characteristics of the grout.

Any bolt pockets must be grouted prior to grouting between the substrate and the base plate.

Continuous grout flow is essential. Sufficient grout must be prepared before starting. The time taken to pour a batch must be regulated to the time to prepare the next one.

Pouring should be from one side of the void to eliminate any air or pre-soaking water becoming trapped under the baseplate. It is advisable to pour the grout across the shortest distance of travel. The grout head must be maintained at all times so that a continuous grout front is achieved.

PUMPING

Where large volumes have to be placed Conbextra C may be pumped. A heavy duty diaphragm pump is recommended for this purpose. Screw feed and piston pumps may also be suitable. Maximum aggregate size for pumping is 0.3 mm. Ensure the selected pump is capable of pumping this size aggregate.

CURING

On completion of the grouting operation, exposed areas should be thoroughly cured. This should be done by the use of Concure curing membrane and continuous application of water and/or wet hessian.

CLEANING

Conbextra C should be removed from tools and equipment with clean water immediately after use. Cured material can be removed mechanically.

LIMITATIONS

LOW TEMPERATURE WORKING

When the air or contact surface temperatures are 5°C or below on a falling thermometer, warm water (30 - 40°C) is recommended to accelerate strength development.

For ambient temperatures below 10°C the formwork should be kept in place for at least 36 hours.

Normal precautions for winter working with cementitious materials should then be adopted.

HIGH TEMPERATURE WORKING

At ambient temperatures above 35°C cool water (below 20°C) should be used for mixing the grout prior to placement.

ESTIMATING

SUPPLY

Conbextra C and Conbextra Grout Aggregate are available in 20 kg moisture resistant bags.

STORAGE

Conbextra C has a shelf life of 12 months if kept in a dry store in sealed bags. If stored in high temperature and high humidity locations, the shelf life may be reduced.

ADDITIONAL INFORMATION

Parchem provides a wide range of complementary products which include:

- concrete repair – cementitious and epoxy
- grouts and anchors – cementitious and epoxy
- waterproofing membranes – liquid applied, cementitious and bituminous sheet membranes
- waterstops – pvc and swellable
- joint sealants – building, civil and chemical resistant
- industrial flooring systems – cementitious and epoxy
- architectural coatings
- filler boards – swellable cork, bituminous and backing rod
- ancillary products

For further information on any of the above, please consult with your local Parchem sales office.

IMPORTANT NOTICE

A Material Safety Data Sheet (MSDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the MSDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

PRODUCT DISCLAIMER

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

*Manufactured and sold under license from Fosroc International Limited. Fosroc and the Fosroc logo are trade marks of Fosroc International Limited, used under license. *Denotes a trade mark of Fosroc International Limited.

PARCHEM	CONCRETE REPAIR	FLOORING	JOINTING SYSTEMS	WATERPROOFING
TECHNICAL DATA SHEET	SEPTEMBER 07			
www.parchem.com.au	7 Lucca Road, Wyong NSW 2259	Sales 1800 624 322	Technical 1800 812 864	ABN 80 069 961 968 4