

## Concure WB30

**Water based wax emulsion, curing compound - conforms to AS3799 / potable water suitable**

### USES

Concure WB30 provides a spray-on membrane to retain moisture in concrete for effective curing. Used for concreting generally but especially useful for large areas of concrete construction such as runways, motorways or bridgeworks.

### ADVANTAGES

- Reduces surface shrinkage and cracking by eliminating moisture loss from exposed surfaces
- Increases concrete strength and dusting resistance
- Eliminates the need for damp hessian, sand or polythene
- Rapid film formation
- Enables concrete to hydrate more efficiently
- Non-flammable; non-toxic
- Economical

### SPECIFICATION COMPLIANCE

Concure WB30 complies with the requirements of AS3799 - 1998: liquid membrane - forming curing compounds for concrete.

A copy of the certification is available on request.

### DESCRIPTION

Concure WB30 is a low viscosity wax emulsion which incorporates a special alkali reactive emulsion system. This system ensures that the emulsion forms a non penetrating continuous film immediately upon contact with a cementitious surface. This impervious film prevents excessive water evaporation which in turn permits more efficient cement hydration thus reducing shrinkage and increasing durability.

### DESIGN CRITERIA

To achieve the correct curing properties, Concure WB30 must be applied on to the substrate at the coverage rate recommended.

an  company

### PROPERTIES

Data quoted typical for this product, but does not constitute a specification.

	Concure WB30 Clear	Concure WB30 White
<b>Weight solids:</b>	31%	32%
<b>Specific gravity at 20°C:</b>	0.968	1.00
<b>Drying time:</b>	2 - 3 hours	2 - 3 hours
<b>Colour (wet):</b>	White	White
<b>Colour (dry):</b>	Clear	White
<b>Efficiency:</b> AS3799	91%	93%
<b>Viscosity:</b>	Brookfield #2, 60 RPM at 25°C. Both grades 65 - 250 cP	
<b>Minimum application temperature:</b>	5°C	

Membrane break down: (applicable to both grades). The rate of degradation will depend upon initial membrane thickness and the degree of exposure to ultra violet light.

Light reflectance: 62% for white pigmented (must be more than 60%) ASTM 309-74.

### SPECIFICATION CLAUSES

#### CONCRETE CURING COMPOUND

All designated areas are to have a liquid curing compound applied to the freshly finished concrete. The curing compound will be based on wax emulsion, have a water retention efficiency of not less than 90% when tested to AS3799 and have a weight solids content of not less than 30%. Such a material is Fosroc Concure WB30 as supplied by Parchem. The curing compound is to be applied in accordance with the manufacturers application instructions.

### APPLICATION INSTRUCTIONS

Concure WB30 should be thoroughly mixed prior to use and spray applied to the surface of newly placed concrete. The



<b>PARCHEM</b>	CONCRETE REPAIR	<b>FLOORING</b>	JOINTING SYSTEMS	WATERPROOFING
<b>TECHNICAL DATA SHEET</b>	<b>JANUARY 08</b>			
<a href="http://www.parchem.com.au">www.parchem.com.au</a>	7 Lucca Road, Wyong NSW 2259	Sales 1800 624 322	Technical 1800 812 864	ABN 80 069 961 968

# Concure WB30



compound should be applied as soon as possible after the concrete is free from surface water. The nozzle of the spray should be held approximately 450 mm from the concrete surface and should be passed back and forth to ensure complete coverage. The pump pressure should be maintained at a level producing a fine spray.

Concure WB30 should not be continuously re-circulated through high shear gear pumps when used in concrete train application. If continuous re-circulation is essential the sprayer should be fitted with a low shear diaphragm pump.

Rate of application should be 5.0 m<sup>2</sup>/litre.

## EQUIPMENT

For the application of Concure WB30, various types of spraying equipment can be used, i.e. knapsack or motorised sprays.

## CLEANING

Immediately after use the spraying equipment should be cleaned out with water. If the spray nozzle becomes blocked with wax particles these can be easily removed using white spirit or similar fluid.

## LIMITATIONS

Concure WB30 must not be used as a curing aid on surfaces subjected to after trade treatments.

Do not brush on to soft, wet concrete or render surfaces which will be disturbed and thus prevent formation of the curing film.

Concure WB30 should not be used as the curing compound for any metallic based integral floor hardeners. Concure CR or Concure HR90 should always be used to prevent rusting of the metallic aggregate.

## ESTIMATING

### SUPPLY

**Concure WB30:** 20 and 200 litre drums

### COVERAGE

**Concure WB30:** 5.0 m<sup>2</sup> per litre

The coverage figures given are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

## STORAGE

Concure WB30 has a shelf life of 18 months when stored at temperatures between 4°C and 35°C. Containers should be kept airtight to prevent surface evaporation. Freezing or prolonged exposure to direct heat or direct sunlight must also be avoided.

## ADDITIONAL INFORMATION

Parchem provides a wide range of complementary products which include:

- concrete repair – cementitious and epoxy
- grouts and anchors – cementitious and epoxy
- waterproofing membranes – liquid applied, cementitious and bituminous sheet membranes
- waterstops – pvc and swellable
- joint sealants – building, civil and chemical resistant
- industrial flooring systems – cementitious and epoxy
- architectural coatings
- filler boards – swellable cork, bituminous and backing rod
- ancillary products

For further information on any of the above, please consult with your local Parchem sales office.

## IMPORTANT NOTICE

A Material Safety Data Sheet (MSDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the MSDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

## PRODUCT DISCLAIMER

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

\*Manufactured and sold under license from Fosroc International Limited. Fosroc and the Fosroc logo are trade marks of Fosroc International Limited, used under license. \*Denotes a trade mark of Fosroc International Limited.

an alesco company



<b>PARCHEM</b>	CONCRETE REPAIR	<b>FLOORING</b>	JOINTING SYSTEMS	WATERPROOFING
<b>TECHNICAL DATA SHEET</b>	<b>JANUARY 08</b>			
<a href="http://www.parchem.com.au">www.parchem.com.au</a>	7 Lucca Road, Wyong NSW 2259	Sales 1800 624 322	Technical 1800 812 864	ABN 80 069 961 968 <b>2</b>