



## Latex cement liquid membrane

### Description

Gripset 2P is a two component latex polymer enhanced cementitious membrane designed for waterproofing wet areas, showers, podiums, terraces, balconies, immersed and subterranean areas. Compliant to AS/NZS 4858:2004, Gripset 2P holds CSIRO Technical Assessment No. 347, satisfying the requirements of AS3740 "Waterproofing Wet Areas in Residential Buildings".

Developed by advanced polymer technology, Gripset 2P provides a unique durable membrane while maintaining flexible and permanent waterproofing properties. Gripset 2P is fast drying and possesses high adhesion to a range of substrates while providing outstanding bonding properties to surface finishes such as renders, screeds, and tile adhesives. Suitable for cool or humid environments to enable tiling after 24 hours.



### Features & benefits

- Water based, free of solvents, non toxic and non flammable
- Waterproof, withstanding continuously wet and immersed environments
- Excellent adhesion to surfaces
- Flexible, accommodating normal substrate movement from building surfaces.
- Excellent bonding properties for renders, screeds, tile adhesives and toppings
- Durable and tough
- Can be applied by brush or roller on horizontal and vertical surfaces without sagging
- Low odour and free of dangerous fumes in warm and/or confined areas.

### Application

Gripset 2P is suitable for commercial, industrial and residential applications.

### Waterproofing uses

- Internal wet areas, bathrooms, laundries and tiled areas
- Balconies, decks, podiums, terrace floors
- Parapet and feature walls
- Water features, swimming pools
- Planters, retaining walls, earth shelters
- General tiled areas to prevent moisture ingress

### Substrates

Substrates suitable for bonding Gripset 2P over include:

- Concrete, render and masonry
- Fibre cement sheeting, plasterboard and structural sheeting
- Wet area timber sheeting and external grade plywood
- Aerated concrete panels and blocks

For further information on suitable surfaces and substrates contact technical department of Gripset Industries for correct advice on surface preparation and suitability.

### Surface preparation

Surfaces must be prepared thoroughly before commencing application. All substrates must be structurally sound, stable, dry, and clean, with substrate compressive strength a minimum 25MPa and cohesive strength a minimum 1.5MPa. Rough surfaces are to be evened or filled first (refer to Gripset 11Y). Building surfaces must be constructed to manufacturer's recommendations and relevant building standards in force at time of membrane application. All surfaces are to be free of sharp protruding surfaces, loose material, de-bonded coatings, curing membranes/agents, release agents, wax residues, foreign particles, laitance, algae and moss, grime, oils, animal fats or grease remains.

Structurally unsound layers and surface contaminants are to be mechanically removed by abrasive blasting, blast tracking, grinding or equivalent methods. For thorough surface preparation, refer to Gripset SC (algae and moss remover) and Gripset DG (water based oil degreaser) products.

### Priming

Gripset 2P membrane must be applied onto primed surfaces:

- Gripset GP primer – for general vertical and horizontal building surfaces. Brush or roller apply primer to total surface area at a minimum coverage of 1 litre per 5m<sup>2</sup> and allow drying for 30 minutes or once wet film dries to a clear transparent coating.
- Gripset P10 primer – for surfaces with residual or rising damp (refer to product data). Apply by brush or roller in 2 coats at a minimum coverage of 1 litre per 3m<sup>2</sup>, ensuring subsequent coat is applied in opposite direction to the first coat. Allow to dry for a minimum 6 hours before applying membrane. Primer must be tack free before applying membrane.
- Gripset 11Y slurry – for immersed areas. Mix Gripset 11Y in equal volumes to the following ratios: 1 part Gripset 11Y + 1 part Portland cement + 1 part fine wash sand, mix to form homogenous slurry. Brush apply to substrate at coverage of 1 litre per 3m<sup>2</sup>. Membrane is to be applied over primer slurry while primer is in a damp/wet state, i.e. "wet on wet" application.



## Latex cement liquid membrane

### Detailing

All critical areas such as joints, junctions, movement zones, penetrations and drainage points are to be correctly sealed and detailed prior to membrane application.

<b>Voids, gaps and undulating surfaces:</b>	Filled and evened with Gripset 11Y repair mortar compound.
<b>Cracks up to 1mm:</b>	Filled with Gripset SB flexible sealant
<b>Cracks &gt;1mm:</b>	Filled Gripset SB flexible sealant, followed by Elastoproof Joint Band.
<b>Bond Breaker:</b>	Elastoproof Joint Band to wall/floor junctions and wall/wall junctions.
<b>Movement or Expansion Joints:</b>	Elastoproof Joint Band
<b>Penetrations, Pipes, Drain outlets:</b>	Elastoproof Collars to be used

### Membrane application

#### Mixing

1. Gripset 2P consists of a 10kg liquid component and a 15kg dry powder component. Membrane is formed by mixing 15kg Gripset 2P powder to 10kg Gripset 2P liquid.
2. To mix smaller quantities, measure on parts by volume, mix 1:1 liquid to dry powder.
3. When mixing, slowly add the dry powder component to the liquid, ensuring the mixing of components is continuous while the powder is added. Using an electric/mechanical stirrer with a paddle attachment at a slow-medium speed, mix the dry component until it is evenly dispersed into the liquid and lump free.
4. Allow the mix to settle for 3-5 minutes then re-stir before use. Pot life once mixed is 60-75 minutes; however this may be reduced in warmer weather.

#### General

The application of Gripset 2P must comply with AS3740. Product is to be applied in a minimum of 2 coats at a total minimum coverage of 1.5 litres/m<sup>2</sup>; forming a minimum dried film thickness of approximately 1.2mm. For immersed applications a total minimum coverage of 2 litres/m<sup>2</sup>; forming a minimum dried film thickness of approximately 1.6mm. Apply subsequent coats at different directions to the previous coat. Coverage is dependent upon surface condition and will vary accordingly as uneven and porous surfaces will require greater coverage to achieve the specified film thickness. Product can be applied by roller or brush.

#### Installing Elastoproof Bond breaker Joint Band

Measure and cut Elastoproof Joint Band for all wall/floor junction areas. Apply first coat of Gripset 2P membrane to approximately 150mm extending up walls and on to floors, and embed Elastoproof Joint Band into wet bed of liquid membrane, ensuring fabric edges are fully wet out and no air bubbles exist behind the fabric. Rear rubber section of Elastoproof Joint Band is not bonded to substrates. At sections where Joint Band is to be joined, a minimum 50mm overlap is required. Elastoproof Prefabricated Corners are available for both internal (90°) and external (270°) junctions, enabling Joint Band to overlap and avoid joint at critical areas.

If Prefabricated corners are not used, Elastoproof Joint Band is to have bottom leg cut and folded; ensuring fabric is completely bonded with Gripset 2P membrane.

For floor pipes protruding floors, Elastoproof Collars are to be fitted over the neck of the pipe, embedding fabric edges into wet bed of Gripset 2P membrane. For floor wastes that are finished level with the floor, Elastoproof Inverted Collars are to be fitted or alternatively the Gripset 2P membrane with Gripset RF Fabric embedded is to be dressed down into the waste outlet at a minimum 50mm.

Once Elastoproof Joint Band is in place, apply Gripset 2P membrane to the total floor area and to walls at 150mm high in general wet areas and balcony decks, and at 1.8m high in shower alcoves. A continuous seamless membrane should be the final finish to the total area upon completion of the waterproofing membrane application.

### Tiling & surface toppings

- It is recommended when tiling directly over Gripset 2P in internal and external floor areas, that Gripset C-Flex, Gripset C-Bond or Gripset C-Set tile adhesives be used.
- In immersed areas tile directly over Gripset 2P with Gripset C-Set tile adhesive.
- If applying a screed, render or concrete topping over Gripset 2P it is recommended to incorporate Gripset 11Y as a proprietary bonding agent and water resistant additive.
- For use of other adhesives over Gripset 2P contact the technical department of Gripset Industries for detail of compatibility.
- Pre mixed tile adhesives are not recommended to be used over Gripset 2P.
- Drying time before tiling is 24 hours.

**Note:** All tiling is to be carried out to AS3958.1 – 2007 "A Guide To The Installation of Ceramic Tiles"



## Latex cement liquid membrane

- Storage conditions**
- Best stored at room temperature.
  - Avoid cold freezing conditions and off concrete floors.
  - Do not store in direct sunlight.
  - Shelf life: Liquid component is 12 months; powder component is 6 months in original unopened packaging.

- Precautions**
- Not to be used as a trafficable surface
  - Do not apply to areas when rain is imminent
  - Do not apply when surface temperature is below 5°C or above 30°C
  - Not to be applied over glass or glazed surfaces
  - Not designed as a sealant for expansion or control joints
  - Not to be used in areas where solvent or petroleum based products may be spilled
  - Not to be used in areas subject to negative hydrostatic pressure
  - All finish coatings over this membrane must be water based and solvent free
  - Material Safety Data sheet (**MSDS**) available
  - For further information contact technical department of Gripset Industries

- Packaging**
- Liquid Component – 10 litres (in a 15 litre oval pail with spout); 200 litre drums
  - Dry Powder Component – 15kg bag

- Clean up**
- In water while wet.
  - Once dried product needs to be removed mechanically.

**Technical data**

<b>Appearance</b>	Liquid – white; Dry – light grey
<b>Form</b>	When mixed – off white viscous paste When dried – grey/olive appearance
<b>Drying</b>	Tack free: 45-60 minutes Re-coat: 2-4 hours Dry film: 8-10 hours Tiling or toppings over: 24 hours Immersion: 7 days curing
<i>Based on normal ambient conditions of 20°C</i>	
<i>* Temperature, humidity and porosity will vary dry times</i>	
<b>Mixing ratio</b>	1 parts liquid : 1 parts dry (by volume)
<b>Specific gravity of mixed product</b>	1.25kg/litre
<b>Shore A Hardness (ASTM D2240-97)</b>	92

**Durability test results for AS/NZS 4858 – 2004:**

<b>Elongation</b>	239%
<b>Classification</b>	Class II
<b>Tensile Strength</b>	1MPa
<b>Water Immersion Test - 56 Days</b>	PASS
<b>Bleach Immersion Test - 56 Days</b>	PASS
<b>Detergent Immersion Test - 56 Days</b>	PASS
<b>Heat Ageing</b>	PASS
<b>Cyclic Movement Test</b>	PASS
<b>Water Absorption Test</b>	PASS
<b>Vapour Transmission Test</b>	0.22g/24h/m <sup>2</sup>

**Contact details**

**Gripset Industries Pty Ltd**  
ABN: 41 094 789 929  
Telephone: +61 (8) 8124-7300 or 1800 650 435  
Email: [techenquiries@gripset.com](mailto:techenquiries@gripset.com)  
Website: [www.gripset.com](http://www.gripset.com)

**Product disclaimer**

This Product Data Sheet (PDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this PDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Gripset Industries does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.