

# MasterEmaco<sup>®</sup> 2525 (Formerly known as Concrecive 2525)

Solvent free epoxy binder and structural adhesive

## DESCRIPTION

**MasterEmaco 2525** is a solvent free, high performance, versatile epoxy binder that can be used to produce a range of epoxy resin based mortars. **MasterEmaco 2525** can be applied to both dry and damp surfaces and adheres to most substrates after proper preparation.

## RECOMMENDED USES

- Structural bonding of new to old concrete
- Production of epoxy resin mortars for floor toppings
- Production of epoxy resin mortars to grout bolt holes
- Steel bonding
- Rapid structural repair of concrete
- Grouting dowels
- Priming of concrete floors prior to applying Mastertop Flooring Systems and MasterSeal Membrane Systems to achieve structural bond

## FEATURES AND BENEFITS

- **Adheres to wet or damp surfaces** - Wide application area
- **Solvent free** - Low VOC and non-shrink
- **Pre-proportioned packaging** - No job site errors
- **Multi-purpose binder** - Many uses
- **Low viscosity** - Easy to apply as primer
- **High abrasion and chemical resistance** - Can be used as wearing surface
- **Approved to AS/NZS 4020:2002** - Suitable for contact with Potable Water
- **Cures hard at low temperatures** - Wide application range

## PROPERTIES

Mixed resin and hardener only	@ 23°C
Compressive Strength 7 days	95 MPa
Flexural strength 7 days	40 Mpa
Tensile strength 7 days	60 MPa
Compressive Strength 24 hrs	58 MPa
Heat deflection temp	80°C

Compressive modulus	3.4 GPa
Bond strength	>2.5 MPa (concrete failure)
Abrasion Resistance ASTM C779	0.24mm/30 mins.
<b>Mortar Performance (A+B+filler)</b>	<b>@ 23°C</b>
Fluid Grout F1 Filler	
Compressive strength	80MPa
Tensile strength	50MPa
Flowable Mortar F1 Filler	
Compressive strength	75MPa
Tensile strength	42MPa
Mortar F1 Filler	
Compressive strength	64MPa
Tensile strength	36MPa

## Chemical Resistance

**MasterEmaco 2525** resists most common organic and inorganic acids in diluted form, also resistant to alkalis, water, oils, grease, etc. Chemical resistance depends on the chemicals involved, their concentration, temperature and degree of exposure. Good housekeeping practices such as immediate clean-up of all spillages will greatly extend the service life.

	Part A	Part B	Mixed
<b>Supply Form</b>	Liquid	Liquid	Liquid
<b>Colour</b>	Clear	Amber	Amber
<b>Mix Ratio</b>			3:1 pbv
<b>Density (Mixed)</b>			1.1kg/L
<b>Application Temperature: 5°C - 35°C</b>			

## APPLICATION

### Surface preparation

Remove all grease, oil, dust, residual curing



The Chemical Company

# MasterEmaco<sup>®</sup> 2525 (Formerly known as Concessive 2525)

compound, mould release agent or other contaminant that could impair adhesion. Laitance should preferably be removed by light sweep blasting or hydro-jetting. Mechanical wire brushing may be appropriate for small areas.

Spalled concrete should be cut back to sound concrete and made good with **MasterEmaco 2525** mortar. Conventional concrete curing compounds should be removed before application.

## Mixing

Proportion part kits accurately mixing only what can be used in less than 30 minutes. Thoroughly stir Part A, add Part B (3:1 parts by volume respectively) and blend thoroughly using a slow speed mixer fitted with a suitable paddle. When being used as a grout or mortar, only clean kiln dried sand may be mixed in. The maximum aggregate size should approximate to 1/3 of the minimum required depth. Add Mastertop X1 colour packs into floor screeds to ensure colour throughout flooring system. The following mix ratios are given as a guide. Consideration should be given to the volume of mortar and potential problems associated with exothermic reactions.

## Application

The **MasterEmaco2525** mortar or grout may be placed on to the surface using standard grouting or trowelling techniques.

Note: The surface needs to be primed when using "dry" mortars. Use **MasterEmaco2525** Binder only to prime and apply wet on wet, when aggregate ratio is over 1-3, resin to aggregate. Should **MasterEmaco 2525** cure when priming, seed with F1 or F5 Filler.

## Curing

Cure time will vary depending on the ambient temperature, quantity mixed and placed, and the rate of sand addition. **MasterEmaco 2525** will have fully cured after 7 days at 23°C.

### ESTIMATING DATA

For 1 litre of binder volume of F1 filler		Total Yield
Grout	2 litres	2.25 litres
Flowable Mortar	3 litres	3 litres
Mortar	4 litres	4 litres

Priming: coverage 4-6m<sup>2</sup>/litre.

Wet to dry bonding concrete: approximately 4m<sup>2</sup>/litre depending on profile of concrete.

### PACKAGING

**MasterEmaco 2525** comes in 2 litre, 5 litre and 20 litre kit sizes

### SHELF LIFE

**MasterEmaco 2525** can be stored in tightly closed original containers for 24 months at moderate temperature.

### PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

ID# MasterEmaco 2525 ANZ V1.1 0113

#### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

#### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

#### BASF Australia Ltd

ABN 62008437867  
Construction Chemicals Division  
11 Stanton Road Seven Hills, NSW 2147

#### Sales Offices:

Sydney, Brisbane, Melbourne,  
Adelaide, Perth  
**Freecall: 1300 227 300**

#### BASF Emergency Advice:

1800 803 440 within Australia (24hr)  
0800 944 955 within New Zealand

#### BASF New Zealand Ltd

45 William Pickering Drive, Albany, Auckland, Phone: 0800 334 877

#### BASF WEB SITES

www.basf-cc.com.au      www.basf-cc.co.nz