

SIGMACOVER 280

6 pages

October 2012
Revision of November 2010

Description two component polyamide cured epoxy primer

PRINCIPAL CHARACTERISTICS

- general purpose epoxy primer in protective coating systems for steel and non ferrous metals
- good adhesion to steel and galvanised steel
- good adhesion to non ferrous metals
- good flow and wetting properties
- good water and corrosion resistance
- cures at temperatures down to +5°C
- suitable for touching up of weld seams and damages of epoxy coatings during construction
- excellent recoatability
- can be overcoated with most alkyd-, chlorinated rubber-, vinyl-, epoxy- and two component polyurethane coatings
- suitable on wet blast cleaned substrates (damp or dry)
- compatible with well designed cathodic protection systems

COLOURS AND GLOSS yellow/green (redbrown on request) – eggshell

BASIC DATA AT 20 °C (1 g/cm³ = 8.35 lb/US gal; 1 m²/l = 40.7 ft²/US gal)
(data for mixed product)

Mass density	1.3 g/cm ³
Volume solids	57% ± 2%
VOC (Directive 1999/13/EC, SED)	max. 327 g/kg (Directive 1999/13/EC, SED)
VOC (UK PG 6/23(92) appendix 3)	max. 432 g/l (approx. 3.6 lb/gal) (UK PG 6/23(92) Appendix 3)
Recommended dry film thickness	50 - 100 µm depending on system
Theoretical spreading rate	11.4 m ² /l for 50 µm 5.7 m ² /l for 100 µm *
Touch dry after	1.5 hour at 20 °C
Overcoating interval	min. see tables * max. see tables *
Full cure after	7 days * (data for components)
Shelf life (cool and dry place)	at least 24 months * see additional data

SIGMACOVER 280

October 2012

**RECOMMENDED
SUBSTRATE CONDITIONS
AND TEMPERATURES**

- **for immersion exposure:**
 - steel or steel with not approved zinc silicate shop primer; blast cleaned (dry or wet) to ISO-Sa2½, blasting profile 30 - 75 µm
 - steel with approved zinc silicate shop primer; weld seams and areas of damaged shop primer or breakdown should be blast cleaned to ISO-Sa2½, blasting profile 30 - 75 µm or power tool cleaned to SPSS-Pt3
 - coated steel; hydrojetted to VIS WJ2 L (blasting profile 30 - 75 µm)
- **IMO-MS.C.215(82) Requirements for Water Ballast Tanks:**
 - steel; ISO 8501-3:2006 grade P2, with all edges treated to a rounded radius of minimum 2 mm or subject to three pass grinding
 - steel or steel with not approved zinc silicate shop primer; blast cleaned to ISO-Sa2½, blasting profile 30 - 75 µm
 - steel with approved zinc silicate shop primer; weld seams and areas of damaged shop primer or breakdown should be blast cleaned to ISO-Sa2½, blasting profile 30 - 75 µm
 - for shop primer with IMO type approval; no additional requirements
 - for shop primer without IMO type approval; blast cleaned to ISO-Sa2 removing at least 70% of intact shop primer, blasting profile 30 - 75 µm
- dust quantity rating "1 for dust size class "3", "4" or "5", lower dust size classes to be removed if visible on the surface to be coated without magnification (ISO 8502-3:1992)
- **for atmospheric exposure conditions:**
 - steel; blast cleaned to ISO-Sa2½, blasting profile 30 - 75 µm or according to ISO-St3
 - shop primed steel; pretreated to SPSS-Pt3
 - galvanised steel; cleaned from grease, salts, contamination and roughened up
- substrate temperature should be above 5°C and at least 3°C above dew point during application and curing
- maximum relative humidity during application and curing is 85%

SYSTEM SPECIFICATION

- marine system sheets: 3101, 3102, 3103, 3104,
3105, 3106 (spec. 5,7), 3107, 3108

SIGMACOVER 280

October 2012

INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 80 : 20

- the temperature of the mixed base and hardener should preferably be above 15°C, otherwise extra solvent may be required to obtain application viscosity
- too much solvent results in reduced sag resistance and slower cure
- thinner should be added after mixing the components

Induction time

none

Pot life

8 hours at 20 °C *

* see additional data

AIR SPRAY

Recommended thinner

Thinner 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.5 - 2 mm

Nozzle pressure

0.3 - 0.4 MPa (= approx. 3 - 4 bar; 44 - 58 p.s.i.)

AIRLESS SPRAY

Recommended thinner

Thinner 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

approx. 0.46 mm (= 0.018 in)

Nozzle pressure

15 MPa (= approx. 150 bar; 2176 p.s.i.)

BRUSH/ROLLER

Recommended thinner

no extra thinner is necessary,

Volume of thinner

but up to 5% Thinner 91-92 can be added if desired

CLEANING SOLVENT

Thinner 90-53

Film thickness and spreading rate

theoretical spreading rate m ² /l	11.4	7.6	5.7
dft in µm	50	75	100

Maximum dft when brushing:

50 µm

SIGMACOVER 280

October 2012

Overcoating table for SigmaCover 280 for dft up to 100 µm

with various two pack epoxy- and polyurethane coatings

substrate temperature	5°C	10°C	20°C	30°C	40°C
minimum interval	36 hours	16 hours	8 hours	6 hours	4 hours
Max interval when exposed to direct sunshine maximum interval	3 months	3 months	3 months	2 months	2 months
Max interval when not exposed to direct sunshine maximum interval	6 months	6 months	6 months	4 months	3 months

- surface should be dry and free from any contamination

Overcoating table for SigmaCover 280 for dft up to 100 µm

with other types of paint like: most chlorinated rubber-, vinyl-, alkyd coatings

substrate temperature	5°C	10°C	20°C	30°C	40°C
minimum interval	16 hours	10 hours	5 hours	3 hours	2 hours
maximum interval	21 days	21 days	10 days	7 days	4 days

- surface should be dry and free from any contamination
- glossy finishes require a corresponding undercoat

Curing

Curing table for dft up to 100 µm

substrate temperature	touch dry	dry to handle	full cure
5°C	8 hours	13 hours	21 days
10°C	4 hours	6 hours	14 days
20°C	2 hours	2.5 hours	7 days
30°C	1 hour	1.5 hour	5 days
40°C	45 min.	1 hour	3 days

- adequate ventilation must be maintained during application and curing (please refer to sheets 1433 and 1434)

SIGMACOVER 280

October 2012

Pot life (at application viscosity)

15 °C	10 hours
20 °C	8 hours
30 °C	5 hours
35 °C	4 hours

Worldwide availability

Whilst it is always the aim of Sigma Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances.

Under these circumstances an alternative product data sheet is used.

REFERENCES

Conversion labels	see information sheet 1410
Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Safe working in confined spaces	see information sheet 1433
Directives for ventilation practice	see information sheet 1434
Cleaning of steel and removal of rust	see information sheet 1490
Specification for mineral abrasives	see information sheet 1491
Relative humidity - substrate temperature - air temperature	see information sheet 1650
PPG Protective & Marine Coatings Ballast Tank Working Procedure New Building	

SAFETY PRECAUTIONS

- for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets
- this is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

SIGMACOVER 280

October 2012

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product.

THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG.

Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT.

The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings products are maintained at www.ppgpmc.com.

The English text of this data sheet shall prevail over any translation thereof.

	PDS	7417
179083	yellow/green	4009002200 (144497 base, 142014 hardener)
179085	redbrown	6137002200 (144493 base, 142014 hardener)