

# Product Data



## 369 UAE-Urethane Additive for Enamel

### PRODUCTS

369-9201

369 UAE Urethane Additive for Enamel

### Product Description

369 UAE is a high performance aliphatic isocyanate resin solution used as an additive to 363 Automotive Enamel, 342 Spraying Enamel and 304 Equipment Enamel to improve drying, hardness, chemical resistance, gloss and durability.

### Packaging

369 UAE is available in 250ml and 500ml packs.

### Mixing

- Add 500ml of 369 UAE to 4 litres of 363 Automotive Enamel
- Add 500ml of 369 UAE to 4 litres of 342 Spraying Enamel
- Add 250ml of 369 UAE to 4 litres of 304 Equipment Enamel

### Precautions

Addition of 369 UAE to either enamel converts that material into a 2-pack urethane enamel containing volatile organic isocyanate. All precautions relative to the handling, mixing and spraying of 2-pack urethane enamels must be adhered to.

369 UAE must be kept firmly sealed as it deteriorates rapidly on exposure to air. If using only portion, reseal container thoroughly after use and plan to use the remainder as soon as possible.

## Health and Safety

Please refer to Material Health and Safety Datasheets for full health and safety details.

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Drying times quoted are average times at 20°C/68°F. Film thickness, humidity and shop temperature can all affect drying times.



PROTEC PTY LTD  
97-105 Bedford Street  
Gillman SA Australia 5013  
Tel: 08 8447 6311  
Fax: 08 8447 6692

PROTEC NZ LIMITED  
327b Neilson Street, Penrose  
Auckland New Zealand  
Tel: 0011 64 9 634 6718  
Fax: 0011 64 9 634 8203