

Fastset C

Fast setting repair mortar for concrete pavements and floors

DESCRIPTION

Fastset C is a pre-packed cementitious mortar specifically formulated for the quick and reliable repair of damaged concrete pavements and industrial floors. The specially selected cements and hard wearing aggregates contained in Fastset C allows the application of large areas with exceptional adhesion to concrete and masonry materials with negligible shrinkage.

Fastset C may be used as a trafficable topping for existing concrete surfaces.

ADVANTAGES

- Good adhesion
- High Strength
- Easy application
- Durable
- Accepts pedestrian and vehicular traffic

TYPICAL PROPERTIES	
Set Times @ 20°C	
Initial	125 minutes
Final	230 minutes
Compressive Strength	
1 day	30 MPa
7 days	50 MPa
28 days	55 MPa
Trafficking Time	
Pedestrian	24 hours
Light Vehicles	48 hours
Minimum application depth	12mm
Maximum application thickness	50mm

APPLICATION INSTRUCTIONS

Preparation

All contacted surfaces must be free of oil, grease or other contamination which may inhibit bond. Any cracked or weakened concrete should be removed prior to being repaired to provide a solid foundation.

Scabbling or water blasting should be used to remove laitance and provide a mechanical key.

The repair area should be carefully delineated. A minimum application depth of 12mm is required. This may necessitate saw cutting and breaking out some material to ensure feather edging does not occur.

Priming

Priming with Rendergrip A is essential to ensure good adhesion and optimum build. Where the substrate is very porous pre-dampening with water may be required. Free water on the surface will reduce the bond and ultimate strength.

Mixing

Fastset C is suitable for mixing using a drill and suitable paddle or by hand where only a small quantity is required. Use 1.6 - 1.8 litres of water per bag of Fastset C to achieve a smooth, soft mortar consistency. Excess water will reduce the final strength and make application of the screed more difficult. Always add the powder to the water while mixing slowly to avoid lumps. Only mix that quantity of material that can be used within the setting time. Do not attempt to rework or re-temper any partially set product.

Application

Apply the mixed Fastset C to the substrate using a trowel to give the required finished thickness. The maximum thickness applied in any application should be limited to 50 mm. Feather edging should be avoided in patch repairs by saw cutting the edge of repairs to a depth of 12mm.

Curing

The application of a thin coat of Rendergrip A as a curing membrane will reduce premature drying in repairs.

Where repairs are subject to direct sun or strong winds the use of Curecon PW is recommended.

CLEAN UP

Clean all equipment with water immediately after use.

Cured Fastset C can only be removed by mechanical means

ESTIMATING

Packaging

Fastset C is supplied in 20 kg bags. Rendergrip A is supplied in 5 and 20 litre containers.

Estimating Data

A 20 kg bag of Fastset C will cover approximately 1.0 m² at an average thickness of 10mm.

Rendergrip A is used at 5 to 7 m² per litre. A scabbled surface will reduce the area covered by the primer and topping.

PRECAUTIONS

Where temperatures less than 5°C or greater than 35°C are encountered, contact our Technical Staff for specific advice.

Do not attempt to re-temper partially set product.

Heavy rain occurring before initial set may damage the surface of Fastset C. Where rain is expected, exposed Fastset C should be protected

STORAGE

Fastset C is a cement based product which must be stored in a dry area off the ground.

Fastset C should be used within 12 months of date of manufacture.

HEALTH AND SAFETY

Fastset C is non-toxic, but it is alkaline in nature. Any contact with eyes or skin should be washed off with clean water.

Protective gloves and clothing should be worn during preparation, mixing and application.

For more detailed information, please read the MSDS for this product.

TECHNICAL SUPPORT

ITLS manufactures a comprehensive range of high quality, high performance construction products. In addition, ITLS offers technical support and on-site advice to specifiers, end users and contractors.

Please contact your ITLS sales representative or ITLS Head Office for this service

ALLIED PRODUCTS

ITLS manufactures a broad range of products under the Aftek brand, which are used in the construction industry and in manufacturing, including:

Grouts

Coatings

Admixtures

Adhesives

Sealants

Floor Toppings

Floor Levelling Compounds

Concrete Repair

Concrete Curing

The information and any recommendations relating to the application and end-use of all ITLS products are provided in good faith based on ITLS's knowledge and experience of the products. In applications, the differences in materials, and variances of substrates and actual site conditions can vary such that no warranty in respect of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be taken as inferred either from this information, or from any written recommendations, or from any other advice offered by ITLS. The proprietary rights of third parties must be observed. All orders are accepted subject to our sale terms and conditions. All users should always refer to the most recent and up to date issue of the Technical Data Sheet for the product concerned, which is available on request. It is recommended that products should always be properly stored, handled and applied under tested and recommended conditions.
PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.



For Further Information
250 Princes Highway
Dandenong Vic 3175
Phone: 1800 651 631 Fax: 1800 672 270
(ABN 41 139 650 883)

Product:	Fastet C
Issue Date:	September 2011
Issue No:	2
Division:	Construction
Total Pages:	2